

## Technical Data Sheet

### Sanitary Silicone Sealant

Suitable for sealing joints and cracks in kitchens, bathrooms, for sealing and bonding of non-porous vitreous surfaces. Ideal for sealing in wet areas. It has high water resistance, temperature resistance. Over time it does not become darkened. It contains anti-fungal additives. Thermostable in the range from  $-50^{\circ}\text{C}$  to  $+180^{\circ}\text{C}$ . Film formation time 15-25 minutes. The time of completely drying 24-48 hours (the seam 5 mm).

#### DIRECTIONS FOR USE:

Clean the surface from dust, grease and other contaminants. Cut the cartridge tip and screw the nozzle tip, cut it in relation to the desired seam width. Using the gun put sealant evenly over the seam. The optimum bead width of 5 mm. Use at temperatures between  $+5^{\circ}\text{C}$  to  $+40^{\circ}\text{C}$ . Store in a cool, dry room and out of reach of children. Avoid direct sunlight and artificial radiation heaters.

#### PRECAUTIONARY MEASURES:

Harmful if inhaled. Irritating to eyes and skin. After contact with the sealant on the skin, rinse with water and, if necessary, consult a doctor.

The date of manufacture is indicated on the bottle.

Shelf life - 18 months.

# PROXY

PROXY UKRAINE LTD

UKRAINE, DNEPROPETROVSK  
AIRPORT STR, 37  
TEL/FAX: +38 (056) 375 85 15

PROXY@3G.UA  
PROXY.UKR.OFFICE@GMAIL.COM

[WWW.PROXY-UKRAINE.COM](http://WWW.PROXY-UKRAINE.COM)

## TECHNICAL DATA:

NO.	Item	Data
1	Base	Acetoxy
2	Density	0,92-0,95 g/cm <sup>3</sup>
3	Color	white, transparent , brown, beige, grey, anthracite
4	Skin formation	15-25 minutes
5	Cutting time (5mm bead)	12-24 hours
6	Curing time	24-48 hours
7	Elongation at break	>450%
8	Shelf life	18 months
9	Application temperature	from +5°C to +40°C
10	Temperature resistance	from -50°C to +180°C

